



PLH+C-Pure Lead Carbon

PLH+C 170FT (12V170Ah)




Specifications

Rated Voltage	12V	
Nominal Capacity	C ₁₀ , 1.80V/cell	170Ah
	C ₈ , 1.75V/cell	170Ah
Dimension	Length	559±1mm (22.01 inches)
	Width	125±1mm (4.92 inches)
	Container Height	320±1mm (12.6 inches)
	Total Height	320±1mm (12.6 inches)
Approx. Weight	54.2 Kg (119.5 lbs)	
Terminal	M8	
Container Material	PC-ABS flame retardant jar and cover to UL94 V-0	
Rated Capacity (25°C)	170.0 Ah	(10hr, 17.0A, 1.80V/cell)
	170.4 Ah	(8hr, 21.3A, 1.75V/cell)
	166.5 Ah	(5hr, 33.3A, 1.75V/cell)
	135.9 Ah	(3hr, 45.3A, 1.75V/cell)
	115.6 Ah	(1hr, 115.6A, 1.67V/cell)
Max. Discharge Current	2040A	
Internal Resistance (25°C)	Approx. 3.2mΩ(Fully charged)	
Operating Temp.Range	-40 ~ 65°C (-40 ~ 149°F)	
Nominal Operating Temp. Range	25±3°C (77±5°F)	
Max.Charging Current(25°C)	Normal Charge 0.3C	
Charge voltage(25°C)	Float	13.62V
	Temp. Coefficient	-3mV/cell/°C
	Equalization	14.1~14.4V
Effect of temp. to Capacity	40°C (104°F)	103%
	25°C (77°F)	100%
	0°C (32°F)	86%
Self Discharge	PLH+C series batteries can be stored up to 24 months at 25°C(77°F). For higher temperatures the time interval will be shorter. Battery needs to be given a freshening charge when the OCV approach 2.10V/cell or when the maximum storage time is reached, whichever occurs first.Storage temp. advised: 0 - 40°C	



Layout



Constant Current Discharge (Amperes) at 25 °C (77° F)

F.V/Time	10 min	15min	20min	30min	45min	1h	2h	3h	4h	5h	8h	10h	20h
1.85V/cell	246.9	212.2	185.3	144.2	110.6	98.6	57.0	42.5	35.7	31.6	20.2	16.8	8.67
1.80V/cell	272.3	233.8	200.9	154.9	117.9	103.7	59.5	44.2	37.0	32.6	20.8	17.0	8.76
1.75V/cell	294.9	249.9	212.9	161.9	122.6	108.8	61.2	45.3	38.3	33.3	21.3	17.3	8.84
1.70V/cell	313.6	263.7	223.0	167.7	126.4	112.2	62.9	46.5	39.1	33.7	21.7	17.7	8.93
1.67V/cell	322.6	270.6	228.0	170.5	128.2	115.6	64.6	47.6	40.0	34.0	22.1	17.9	9.01
1.60V/cell	336.0	281.3	235.7	174.9	130.9	119.0	65.5	48.2	40.4	34.7	22.3	18.0	9.10


Constant Power Discharge (Watts/cell) at 25 °C (77° F)

F.V/Time	10 min	15min	20min	30min	45min	1h	2h	3h	4h	5h	8h	10h	20h
1.85V/cell	482.6	409.8	358.4	281.3	217.3	196.4	119.6	94.7	77.0	64.1	42.8	35.0	18.8
1.80V/cell	522.9	444.9	388.4	302.6	232.6	200.6	125.7	96.8	78.9	65.7	43.9	36.1	19.3
1.75V/cell	559.0	466.1	406.6	313.2	239.6	204.7	128.7	98.0	79.8	66.5	44.5	36.2	19.6
1.70V/cell	589.6	483.4	420.7	321.4	245.0	208.5	130.6	98.9	80.4	66.9	44.6	36.3	19.7
1.67V/cell	604.7	491.5	426.5	325.1	247.6	213.4	131.2	99.1	80.6	67.1	44.8	36.4	19.7
1.60V/cell	629.7	500.5	430.7	327.4	248.4	214.2	131.6	99.2	80.9	67.3	44.9	36.6	19.8



PLH+C-Pure Lead Carbon

PLH+C 170FT (12V170Ah)



Applications

- Backup Power
- Telecom base station with unstable mains
- Light hybrid & renewable energy applications


General Features

- 20 years design life(25°C)
- High energy density
- Low internal resistance and self-discharge rate
- Excellent high rate discharge performance in low temperature


Standards

- Compliance with IEC 60896 standards
- Manufactured in Leoch® IATF16949, ISO 18001, ISO 9001 and ISO 14001 certified production facilities


Discharge Characteristics




Temperature in Relation to Capacity



Float Charging Characteristics



Self-discharge Characteristics



Sales Offices Worldwide

China Sales Office

5th Floor, Xinbaohui Bldg., Nanhai Blvd.,
Nanshan, Shenzhen, China. 518052
Tel: +86-755-86036060 (100 lines)
Fax: +86-755-26067269
E-mail: export@leoch.com

HongKong Sales Office

Workshop C, 33/F, TML Tower, No. 3 Hoi Shing Road,
Tsuen Wan, New Territories, Hong Kong
Tel: +852 35786666
Fax: +44 1452 690125
E-mail: sales.hk@leoch.com

Singapore Sales Office

No. 1 Tech Park Crescent,
Singapore 638131
Tel: +65 68636078
Fax: +65 6863 6079
Email: sales.sg@leoch.com

Australia Sales Office

2/29 Tarlington Place, Smithfield. NSW 2164
Australia
Tel: 02 9756 0950
E-mail: sales.au@leoch.com

North America Sales Office

19751 Descartes
Foothill Ranch, CA 92610, USA
Tel: 949-588-5853
Fax: 949-588-5966
E-mail: sales@leoch.us

UK Sales Office

9B Wheatstone Court, Waterwells, Business Park,
Gloucester, GL2-2AQ, UK United Kingdom
Tel: +44(0) 1452 729428 / 1452 729696
Fax: +44 1452 690125
E-mail: Sales.Europe@leoch.com

EMEA Sales Office

1 Deligiorgi St., 121 31 Athens,
Greece
Tel: +30 210 5760318 (2 lines)
E-mail: support_EMEA@leoch.com

India Sales Office

Shed no. A-53(b), 2nd Stage of Peenya Industrial Area,
Bangalore North Taluk, Bangalore-560058, India
Tel: +91-80-23440018/23440019
Fax: +91-80-23440017
E-mail: indiasales@leoch.com



[Http://www.leoch.com](http://www.leoch.com)
[Http://www.leoch.us](http://www.leoch.us)

© 2021 LEOCH. All rights reserved.
Trademarks and logos are the property of LEOCH and its affiliates unless otherwise noted.
Subject to revisions without prior notice.

Publication No.: LB-PLH+C 170FT-PD-EU-V1.0-202103